

# EVATANE® 18-150

## Ethylene – Vinyl Acetate (VA) copolymer with high VA content

### DESCRIPTION

EVATANE® 18-150 is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radical polymerization process.

### TYPICAL PROPERTIES

| Characteristics              | Value   | Unit              | Test Method            |
|------------------------------|---------|-------------------|------------------------|
| Vinyl Acetate content        | 17-19   | % Wt              | FTIR (Internal Method) |
| Melt Index (190°C / 2.16 kg) | 135-175 | g/10min           | ISO 1133 / ASTM D1238  |
| Density (23°C)               | 0.94    | g/cm <sup>3</sup> | ISO 1183               |
| Melting point                | 88      | °C                | ISO 11357-3            |
| Vicat softening point (10N)  | 43      | °C                | ISO 306 / ASTM D1525   |
| Ring & Ball temperature      | 102     | °C                | ASTM E28 / NF EN 1238  |
| Elongation at break          | 300-500 | %                 | ISO 527 / ASTM D638    |
| Tensile strength at break    | 10      | MPa               | ISO 527 / ASTM D638    |
| Hardness Shore A             | 85      | -                 | ISO 868 / ASTM D2240   |

### APPLICATIONS

The high Vinyl Acetate content of EVATANE® 18-150 brings softness, flexibility and polarity. EVATANE® 18-150 is compatible with most tackifying resins and waxes. Combined with a high fluidity, it is an efficient and easy handling product for hot melt adhesives formulations. It can also be used as an additive for crude oil (pour point depressant), bitumen modification and cables compounds.

For more detailed information and recommendations regarding your specific application, please contact your local ARKEMA technical representative.

### PROCESSING

EVATANE® 18-150 can be processed on most conventional equipments used for thermoplastics. It is recommended to avoid melt temperatures above 230°C and to purge the equipment after a run is completed.

**EVATANE®**  
BY ARKEMA

# EVATANE® 18-150

## STORAGE, HANDLING AND SAFETY

EVATANE® 18-150 should be stored in standard conditions and protected from UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the EVATANE® 18-150 is available upon request to your ARKEMA representative or on the web site [evatane.com](http://evatane.com).

## SHELF LIFE

Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

April 2014

The products described in the brochure are not Medical grades designated for Medical Device applications. Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications that are in contact with the body or circulating bodily fluids. Arkema has designated Medical grades to be used for such Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications that are in contact with the body or circulating bodily fluids. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See MSDS for Health & Safety Considerations

**Arkema Functional Polyolefins**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex - France  
[arkema.com](http://arkema.com) – [evatane.com](http://evatane.com)

**ARKEMA**  
INNOVATIVE CHEMISTRY