

KEPSTAN® 6002 PL

Kepstan® PEKK powder coatings are based on polyether-ketone-ketone, from the polyaryl-ether ketone polymer family. This is our highest performance powder coating which can survive exposure to high continuous use temperatures and corrosive environments while maintaining good abrasion resistance. This Kepstan® PEKK coatings grade can be applied via electrostatic spray or fluidized bed dip.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
THERMAL PROPERTIES			
Oxygen Index	38	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Surface Resistivity, 73 °F	1020	Ohm per square	ASTM D257
Dielectric (Electric) Strength	84	kV/mm	IEC 60243-1
OTHER PROPERTIES			
Density	1270	kg/m ³	ISO 1183
POWDER PROPERTIES			
Nature	PEKK	-	ISO 1218
Color	Natural	-	-
Melting Temperature	300 - 305	°C	ISO 1218
POWDER COATING PROPERTIES			
Recommended Coating Thickness	50 - 75	µm	-
Specific Gravity of Coating, 20°C	1.27	-	ISO 1183
Pencil Hardness	5H	-	ECCA T4
Water Absorption, 24h	≤0.6	%	ISO 62-1
Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles	8 - 12	mg	ISO 9352
Dielectric Strength	84	kV/mm	IEC 60243-1
Surface Resistivity	1020	W	ASTM D257
Fire Resistance on coated panel	V-0	-	UL 94

PROCESSING

Coating, Electrostatic Spray, Fluidized Bed Dipping

DELIVERY FORM

Powder

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kepstan® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kepstan.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

KEPSTAN®
BY **ARKEMA**

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018