

KYNAR® 370

Kynar® resins are fluorinated thermoplastic homopolymers.

Kynar® 370 resin is a thermoplastic fluorinated polymer resin. The properties are the same as standard grade: chemical resistance, resistance to UV, low permeation, high purity, excellent mechanical behavior with a higher HDT.

This grade is especially modified in order to have a reduced mold shrinkage, low thermal expansion factor. Moreover, this grade has an increased thermal and electrical conductivity.

This grade is available as pellet form for injection, extrusion, compression.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	5.8	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-
Melt Flow Rate	5 - 17	g/10min	ASTM D1238
Temperature	230	°C	-
Load	3.8	kg	-
Molding Shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding Shrinkage, normal	0.7	%	ISO 294-4, 2577
Melt Viscosity, 230°C, 100 s-1	8 - 13	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus, 73 °F	3100 - 5170	MPa	ASTM D638
Tensile Strength at Yield, 73 °F	34.5 - 55.2	MPa	ASTM D638
Elongation at Yield, 73 °F	0 - 4	%	ASTM D638
Tensile Strength at Break, 73 °F	37.9 - 55.2	MPa	ASTM D638
Elongation at Break, 73 °F	0 - 20	%	ASTM D638
Hardness, Shore D, 73 °F	74 - 79	-	ASTM D2240
Flexural Modulus, 73 °F	5520 - 6890	MPa	ASTM D790
Flexural Strength @ 5% Strain, 73 °F	138 - 207	MPa	ASTM D790
Compressive Strength, 73 °F	138 - 172	MPa	ASTM D695
Unnotched Impact Strength, 73 °F	0.267 - 0.534	kJ/m	ASTM D256
Notched Impact Strength, 73 °F	0.04 - 0.0801	kJ/m	ASTM D256
Coefficient of Friction, Static vs. Steel, 73 °F	0.18	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.12	-	ASTM D1894
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	170	°C	ISO 11357-1/-3
Melting Point, 73 °F	165 - 170	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-40.6 - -38.3	°C	ASTM D7028

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR®
BY ARKEMA

KYNAR® 370

Temp. of Deflection Under Load, 1.80 MPa	120	°C	ISO 75-1/-2
Heat Deflection Temperature, 264 Psi, 248 °F/hr	110 - 127	°C	ASTM D648
Heat Deflection Temperature, 66 Psi, 248 °F/hr	132 - 149	°C	ASTM D648
Coeff. of Linear Thermal Expansion, parallel	40	E-6/K	ISO 11359-1/-2
Coefficient of Thermal Expansion, 73 °F	3.6 - 4.5	10E-5/°C	ASTM D696
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
Limiting Oxygen Index, 73 °F	44	%	ASTM D2863
Thermal Decomposition TGA, in air	375	°C	1% wt. loss
Thermal Decomposition TGA, in nitrogen	410	°C	1% wt. loss
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	33	-	IEC 60250
Dielectric Constant, 1 kHz	28.8 - 33.5	-	ASTM D150
Dissipation Factor, 100Hz	610	E-4	IEC 60250
Dissipation Factor, 100 kHz	0.06 - 0.08	-	ASTM D150
Volume Resistivity	1E11	Ohm*m	IEC 60093
Volume Resistivity, DC 68 °F, 65% R.H.	≥ 1E11	Ohm*cm	ASTM D257
OTHER PROPERTIES			
Water Absorption	0.02	%	Sim. to ISO 62
Specific Gravity, 73 °F	1.84 - 1.88	-	ASTM D792
Density of melt	1880	kg/m³	-

PROCESSING

Injection Molding

DELIVERY FORM

Pellets

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

KYNAR®
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018