

KYNAR® 740E

Kynar® resins are fluorinated thermoplastic homopolymers.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

Kynar® 740 E resin is a standard grade of granules for extrusion of tubes and plaques, compression and transfer molding. This product is ANSI/NSF Standard 61 certified. This product is compliant with the EU positive list.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	1.4	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-
Molding Shrinkage, parallel	2.5	%	ISO 294-4, 2577
Molding Shrinkage, normal	2.5	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	2000	MPa	ISO 527-1/-2
Yield stress	50	MPa	ISO 527-1/-2
Yield strain	9	%	ISO 527-1/-2
Nominal Strain at Break	> 50	%	ISO 527-1/-2
Charpy Notched Impact Strength, +23°C	36	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	169	°C	ISO 11357-1/-3
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Temp. of Deflection Under Load, 1.80 MPa	104	°C	ISO 75-1/-2
Coeff. of Linear Thermal Expansion, parallel	150	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Yellow Card available	yes	-	-
Oxygen Index	42	%	ISO 4589-1/-2
OTHER PROPERTIES			
Water Absorption	0.008	%	Sim. to ISO 62
Density	1780	kg/m ³	ISO 1183
Thermal conductivity of melt	0.19	W/(m K)	-

MAIN APPLICATIONS:

- corrosion protection in the chemical industry
- wire and cable
- coating (painting, co-extrusion)
- water transportation
- off-shore

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR®
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

KYNAR® 740E

PROCESSING

Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Transfer Molding, Thermoforming

DELIVERY FORM

Pellets

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

KYNAR®
BY **ARKEMA**

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com