

KYNAR® ADHEFLON ASP 720

Kynar® resins are fluorinated thermoplastic homopolymers.

This product is used for the co-extrusion of Rilsan® polyamides and Kynar® PVDF resins for the preparation of multilayer tubing or film.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	12.5	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	10	kg	-
Melt Viscosity, 230°C, 100 s-1	1.6	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Elongation at Break, 73 °F	≥ 100	%	ASTM D638
THERMAL PROPERTIES			
Melting Point, 73 °F	166	°C	ASTM D3418
OTHER PROPERTIES			
Density	1270	kg/m ³	ISO 1183

PROCESSING

Film Extrusion, Sheet Extrusion, Other Extrusion

DELIVERY FORM

Pellets

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

KYNAR®
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018