

KYNAR® ADX 111

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

Kynar® ADX 111 resin allows primer less powder coating (direct adhesion to metals after standard surface preparation).

Can be used easily in standard application processes:

- Dip coating in fluidized bed
- Electrostatic spraying
- Hot flocking

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	27	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	2200	MPa	ISO 527-1/-2
Yield stress	54	MPa	ISO 527-1/-2
Yield strain	8	%	ISO 527-1/-2
Nominal Strain at Break	> 50	%	ISO 527-1/-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	169	°C	ISO 11357-1/-3
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Temp. of Deflection Under Load, 1.80 MPa	110	°C	ISO 75-1/-2
Temp. of Deflection Under Load, 0.45 MPa	132	°C	ISO 75-1/-2
Vicat Softening Temperature, 50°C/h 50N	139	°C	ISO 306
Coeff. of Linear Thermal Expansion, parallel	150	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Thickness Tested	1.5	mm	-
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
Oxygen Index	44	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	9	-	IEC 60250
Relative Permittivity, 1MHz	7	-	IEC 60250
Dissipation Factor, 100Hz	320	E-4	IEC 60250
Dissipation Factor, 1MHz	2140	E-4	IEC 60250
Volume Resistivity	2E12	Ohm*m	IEC 60093
Surface Resistivity	> 1E15	Ohm	IEC 60093
Dielectric (Electric) Strength	21	kV/mm	IEC 60243-1

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR®
ADX
BY ARKEMA

KYNAR® ADX 111

Comparative Tracking Index	600	-	IEC 60112
OTHER PROPERTIES			
Water Absorption	0.1	%	Sim. to ISO 62
Humidity Absorption	0.07	%	Sim. to ISO 62
Density	1780	kg/m ³	ISO 1183

MAIN APPLICATIONS:

- corrosion protection in the chemical industry
- wire and cable
- coating (painting, co-extrusion)
- PPA
- off-shore
- attery

PROCESSING

Coating

DELIVERY FORM

Powder

SPECIAL CHARACTERISTICS

Heat Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

KYNAR®
ADX
BY ARKEMA

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com