

KYNAR® ADX 1285-03

Kynar® resins are fluorinated thermoplastic homopolymers.

Kynar® ADX 1285-03 resin is a flexible thermoplastic fluorinated functionalized polymer.

The properties are the same as standard grade: chemical resistance, resistance to UV, low permeation, high purity, excellent mechanical behavior. More over, these grades increase the potential of adhesion on materials as polyamides, polyolefins and can be coextruded.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Yield stress	35	MPa	ISO 527-1/-2
Yield strain	10	%	ISO 527-1/-2
Nominal Strain at Break	> 50	%	ISO 527-1/-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	72	°C	ISO 75-1/-2
Burning Behav. at Thickness h	HB	class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
OTHER PROPERTIES			
Density	1780	kg/m³	ISO 1183

PROCESSING

Other Extrusion, Coating

DELIVERY FORM

Granules

SPECIAL CHARACTERISTICS

Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

KYNAR®
ADX
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018