

KYNAR® ADX 281

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

Kynar® ADX 281 resin allows primer less powder coating (direct adhesion to metals after standard surface preparation).

Can be used easily in standard application processes:

- Dip coating in fluidized bed
- Electrostatic spraying
- Hot flocking

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	25	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	1500	MPa	ISO 527-1/-2
Yield stress	42	MPa	ISO 527-1/-2
Yield strain	10	%	ISO 527-1/-2
Nominal Strain at Break	46	%	ISO 527-1/-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	157	°C	ISO 11357-1/-3
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	10.5	-	IEC 60250
Relative Permittivity, 1MHz	6.5	-	IEC 60250
Dissipation Factor, 100Hz	380	E-4	IEC 60250
Dissipation Factor, 1MHz	2340	E-4	IEC 60250
Volume Resistivity	2E12	Ohm*m	IEC 60093
Surface Resistivity	1E13	Ohm	IEC 60093
Dielectric (Electric) Strength	21	kV/mm	IEC 60243-1
Comparative Tracking Index	600	-	IEC 60112
OTHER PROPERTIES			
Water Absorption	0.1	%	Sim. to ISO 62
Humidity Absorption	0.06	%	Sim. to ISO 62
Density	1770	kg/m ³	ISO 1183

MAIN APPLICATIONS:

- corrosion protection in the chemical industry
- coating (painting, co-extrusion)
- off-shore
- wire and cable
- PPA
- attery

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR®
ADX
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

KYNAR® ADX 281

PROCESSING

Coating

DELIVERY FORM

Powder

SPECIAL CHARACTERISTICS

Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

KYNAR®
ADX
BY **ARKEMA**

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com