

KYNAR® FILM 252 PGM TR

is a flexible thermoplastic fluorinated film. The properties are the same as standard grade: chemical resistance, resistance to UV, low permeation, high purity, excellent mechanical behavior. These films are specially designed for photovoltaic applications.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Stress at Yield, parallel	30	MPa	ISO 527-3
Stress at Yield, normal	30	MPa	ISO 527-3
Strain at Yield, parallel	7	%	ISO 527-3
Strain at Yield, normal	7	%	ISO 527-3
Maximum Stress, parallel	30	MPa	ISO 527-3
Maximum Stress, normal	30	MPa	ISO 527-3
Maximum Strain, parallel	150	%	ISO 527-3
Maximum Strain, normal	150	%	ISO 527-3
Trouser Tear Resistance, parallel	2	N/mm	ISO 6383-1
Trouser Tear Resistance, normal	3	N/mm	ISO 6383-1
ELECTRICAL PROPERTIES			
Dielectric (Electric) Strength	100	kV/mm	IEC 60243-1
OTHER PROPERTIES			
Humidity Absorption	0.2	%	Sim. to ISO 62
Density	1400	kg/m ³	ISO 1183
FILM PROPERTIES			
Type of Extrusion	blown	-	-
Thickness of Specimen	0.025	mm	-

SPECIAL CHARACTERISTICS

Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

KYNAR®
FILM
BY **ARKEMA**

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018