

KYNAR FLEX® 2950-05

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® 2950-05 resin is a pelletized, semi-crystalline VF2 based copolymer. It has been designed for wire and cable applications requiring high flexibility and improved resistance to impact. The low molecular weight allows extrusion conditions that reduce jacket shrink back over fiber optic constructions.

Additional characteristics:

- Excellent thermal stability
- Excellent abrasion resistance
- Excellent chemical resistance
- Impervious to UV degradation
- High Limiting Oxygen Index
- Extremely low smoke emission characteristics

Meets UL910 requirements

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	11.5	cm ³ /10min	ISO 1133
Temperature	232	°C	-
Load	3.8	kg	-
Melt Flow Rate	8 - 25	g/10min	ASTM D1238
Temperature	230	°C	-
Load	3.8	kg	-
Melt Viscosity, 230°C, 100 s-1	6 - 12	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	387	MPa	ISO 527-1/-2
Tensile Modulus, 73 °F	276 - 448	MPa	ASTM D638
Yield stress	17	MPa	ISO 527-1/-2
Tensile Strength at Yield, 73 °F	13.8 - 21.4	MPa	ASTM D638
Yield strain	18	%	ISO 527-1/-2
Elongation at Yield, 73 °F	15 - 25	%	ASTM D638
Nominal Strain at Break	> 50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	20 - 27.6	MPa	ASTM D638
Elongation at Break, 73 °F	200 - 400	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	21 - 25	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	57 - 62	-	ASTM D2240
Flexural Modulus, 73 °F	276 - 414	MPa	ASTM D790
Flexural Strength @ 5% Strain, 73 °F	13.8 - 24.1	MPa	ASTM D790
Compressive Strength, 73 °F	24.1 - 31	MPa	ASTM D695
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
Unnotched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR FLEX®
BY **ARKEMA**

KYNAR FLEX® 2950-05

Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Coefficient of Friction, Static vs. Steel, 73 °F	0.55	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.54	-	ASTM D1894
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	134	°C	ISO 11357-1/-3
Melting Point, 73 °F	130 - 138	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-42.2 - -40	°C	ASTM D7028
Temp. of Deflection Under Load, 1.80 MPa	43	°C	ISO 75-1/-2
Heat Deflection Temperature, 264 Psi, 248 °F/hr	35 - 51.7	°C	ASTM D648
Temp. of Deflection Under Load, 0.45 MPa	57	°C	ISO 75-1/-2
Heat Deflection Temperature, 66 Psi, 248 °F/hr	48.9 - 65.6	°C	ASTM D648
Coefficient of Thermal Expansion, 73 °F	16.2 - 21.6	10E-5/°C	ASTM D696
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Thickness Tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	0.8	mm	-
Oxygen Index	95	%	ISO 4589-1/-2
Limiting Oxygen Index, 73 °F	95	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18	W/(m K)	ASTM D433
Specific Heat	745 - 958	J/(kg K)	DSC
Thermal Decomposition TGA, in air	375	°C	1% wt. loss
Thermal Decomposition TGA, in nitrogen	410	°C	1% wt. loss
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	7.05	-	IEC 60250
Dielectric Constant, 1 kHz	3.8 - 12.1	-	ASTM D150
Dissipation Factor, 100Hz	0.12	E-4	IEC 60250
Dissipation Factor, 100 kHz	0.02 - 0.24	-	ASTM D150
Volume Resistivity	2E12	Ohm*m	IEC 60093
Volume Resistivity, DC 68 °F, 65% R.H.	2E14	Ohm*cm	ASTM D257
Dielectric (Electric) Strength	1.4	kV/mm	IEC 60243-1
Dielectric (Electric) Strength, 73°F	1.1 - 1.3	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption	0.03	%	Sim. to ISO 62
Water Absorption	0.03 - 0.05	%	ASTM D570
Density	1770	kg/m³	ISO 1183

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SJC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR FLEX®
BY **ARKEMA**

KYNAR FLEX® 2950-05

Specific Gravity, 73 °F

1.78 - 1.8

-

ASTM D792

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central
America, Near East/Africa

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar Flex® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

KYNAR FLEX®

BY ARKEMA

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com