

KYNAR FLEX® 3050-52

Kynar Flex® 3050-52 resin is a copolymer of vinylidene fluoride and hexafluoropropylene specifically designed for flexible plenum cables needing low temperature impact properties down to -40°C.

Its main characteristics are:

- Very high flexibility
- High melting point
- Excellent low temperature impact resistance at -40°C

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Flow Rate	2.5 - 7.5	g/10min	ASTM D1238
Temperature	230	°C	-
Load	12.5	kg	-
Melt Viscosity, 230°C, 100 s-1	21 - 26	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	550	MPa	ISO 527-1/-2
Tensile Modulus, 73 °F	552 - 965	MPa	ASTM D638
Yield stress	19	MPa	ISO 527-1/-2
Tensile Strength at Yield, 73 °F	17.2 - 41.4	MPa	ASTM D638
Yield strain	15	%	ISO 527-1/-2
Elongation at Yield, 73 °F	10 - 20	%	ASTM D638
Nominal Strain at Break	> 50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	23.4 - 27.6	MPa	ASTM D638
Elongation at Break, 73 °F	250 - 350	%	ASTM D638
Hardness, Shore D, 73 °F	65 - 70	-	ASTM D2240
Flexural Modulus, 73 °F	483 - 621	MPa	ASTM D790
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	167	°C	ISO 11357-1/-3
Melting Point, 73 °F	160 - 168	°C	ASTM D3418
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Yellow Card available	yes	-	-
Limiting Oxygen Index, 73 °F	42	%	ASTM D2863
ELECTRICAL PROPERTIES			
Dielectric (Electric) Strength, 73°F	1.3 - 1.5	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption	≤ 0.05	%	ASTM D570
Specific Gravity, 73 °F	1.61 - 1.67	-	ASTM D792

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR FLEX®
BY **ARKEMA**

KYNAR FLEX® 3050-52

Density of melt

1650

kg/m³

-

PROCESSING

Other Extrusion

DELIVERY FORM

Pellets

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar Flex® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

KYNAR FLEX®

BY ARKEMA

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com