

KYNAR FLEX® ADX 2250-05E

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® ADX 2250-05 resin is a semi-crystalline flexible functionalized copolymer designed for co-extrusion with other materials to improve interlayer adhesion. It is particularly suited to tubing, pipe and film co-extrusion applications.

Outstanding characteristics: chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical and thermo-mechanical properties.

More over, this grade increases the potential of adhesion on materials as polyamides, polyolefins and can be coextruded.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	6	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-
MECHANICAL PROPERTIES			
Yield stress	12	MPa	ISO 527-1/-2
Yield strain	18	%	ISO 527-1/-2
Nominal Strain at Break	>50	%	ISO 527-1/-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	123	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	33	°C	ISO 75-1/-2
ELECTRICAL PROPERTIES			
Dielectric (Electric) Strength	13	kV/mm	IEC 60243-1
OTHER PROPERTIES			
Water Absorption	0.1	%	Sim. to ISO 62
Density	1790	kg/m ³	ISO 1183

PROCESSING

Film Extrusion, Sheet Extrusion, Other Extrusion, Blow Molding, Transfer Molding

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar Flex® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

KYNAR FLEX®
BY **ARKEMA**

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018