

KYNAR FLEX® LBG

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® LBG resin is a semi-crystalline copolymer. Kynar Flex® LBG is considered a high molecular weight VF₂ based copolymers - specifically designed for application in the lithium ion battery market.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	3.2	cm ³ /10min	ISO 1133
Temperature	232	°C	-
Load	21.6	kg	-
Melt Flow Rate	3 - 8	g/10min	ASTM D1238
Temperature	230	°C	-
Load	21.6	kg	-
Melt Viscosity, 230°C, 100 s-1	34 - 38	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Yield stress	35	MPa	ISO 527-1/-2
Tensile Strength at Yield, 73 °F	35	MPa	ASTM D638
Yield strain	10	%	ISO 527-1/-2
Nominal Strain at Break	> 50	%	ISO 527-1/-2
Elongation at Break, 73 °F	≥ 400	%	ASTM D638
Flexural Modulus, 73 °F	1030	MPa	ASTM D790
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	154	°C	ISO 11357-1/-3
Melting Point, 73 °F	151 - 157	°C	ASTM D3418
OTHER PROPERTIES			
Water Absorption	0.03	%	Sim. to ISO 62
Density	1780	kg/m ³	ISO 1183
Specific Gravity, 73 °F	1.78	-	ASTM D792

DELIVERY FORM

Powder

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar Flex® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

KYNAR FLEX®
BY **ARKEMA**

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018