

KYNAR FLEX® PPA 5300

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® PPA 5300 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of Kynar Flex® PPA 5300 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

This product is also available on a powder form as Kynar Flex® PPA 5301 resin.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	165	°C	ISO 11357-1/-3
Melting Point, 73 °F	≤329	°C	ASTM D3418
OTHER PROPERTIES			
Density	700	kg/m ³	ISO 1183
Bulk Density	0.5 - 0.9	g/cm ³	1% wt. loss

PROCESSING

Film Extrusion, Sheet Extrusion, Other Extrusion

DELIVERY FORM

Granules, Powder

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar Flex® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

KYNAR FLEX®
BY **ARKEMA**

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com