

KYNAR® MG15

Kynar® resins are fluorinated thermoplastic homopolymers.

Kynar® MG15 resin is a crystalline high viscosity polymer of polyvinylidene difluoride. It is an engineering polymer with an outstanding balance of physical strength and high chemical resistance which make it ideal for micro and ultra-filtration membranes for durable water purification and other applications.

Kynar® MG15 resin is soluble in selected solvents and can be used in solution processing applications. It is especially recommended for hollow fiber and flat sheet membranes.

Kynar® MG15 resin has NSF, FDA, and USP Class VI certifications for use in potable water, food processing, and bio-pharma applications.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Viscosity, 230°C, 100 s-1	33 - 39	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus, 73 °F	1380 - 2310	MPa	ASTM D638
Tensile Strength at Yield, 73 °F	44.8 - 55.2	MPa	ASTM D638
Flexural Modulus, 73 °F	1380 - 2310	MPa	ASTM D790
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	168	°C	ISO 11357-1/-3
Melting Point, 73 °F	162 - 172	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
OTHER PROPERTIES			
Water Absorption	≤ 0.04	%	ASTM D570
Density	1.780	kg/m³	ISO 1183
Specific Gravity, 73 °F	1.77 - 1.79	-	ASTM D792
Solution Viscosity, 20°C, #3 Brookfield	≥ 1500	cps	10% NMP Solution Spindle@20 RPM Spindle Viscometer
OPTICAL PROPERTIES			
Refractive Index @ sodium D line	1.42	-	ASTM D542

PROCESSING

Casting

DELIVERY FORM

Powder

SPECIAL CHARACTERISTICS

Food Contact Approval

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

KYNAR®
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018