

KYNAR SUPERFLEX® 2500-25

Kynar Superflex® 2500-25 is a pelletized, semi-crystalline VF2 based copolymer with a high Limiting Oxygen Index (LOI).
Kynar Superflex® 2500-25 is used for extrusion and injection molding applications where high flexibility and/or ductility is required along with extra flame and smoke resistance.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Flow Rate	1 - 15	g/10min	ASTM D1238
Temperature	230	°C	-
Load	3.8	kg	-
Melt Viscosity, 230°C, 100 s-1	9 - 16	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus, 73 °F	241 - 379	MPa	ASTM D638
Tensile Strength at Yield, 73 °F	11.7 - 19.3	MPa	ASTM D638
Elongation at Yield, 73 °F	17 - 25	%	ASTM D638
Tensile Strength at Break, 73 °F	13.8 - 31	MPa	ASTM D638
Elongation at Break, 73 °F	500 - 800	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	28 - 33	mg/1000 cycles	ASTM-G195-13A
Hardness, Shore D, 73 °F	50 - 57	-	ASTM D2240
Flexural Modulus, 73 °F	193 - 276	MPa	ASTM D790
Flexural Strength @ 5% Strain, 73 °F	10.3 - 17.2	MPa	ASTM D790
Compressive Strength, 73 °F	13.8 - 20.7	MPa	ASTM D695
Unnotched Impact Strength, 73 °F	≥ No Break	kJ/m	ASTM D256
Notched Impact Strength, 73 °F	≥ No Break	kJ/m	ASTM D256
Coefficient of Friction, Static vs. Steel, 73 °F	0.49	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.54	-	ASTM D1894
THERMAL PROPERTIES			
Melting Point, 73 °F	117 - 125	°C	ASTM D3418
Glass Transition Temperature (Tg)	-41.7 - -40	°C	ASTM D7028
Coefficient of Thermal Expansion, 73 °F	15.3 - 19.4	10E-5/°C	ASTM D696
Limiting Oxygen Index, 73 °F	≥ 75	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18	W/(m K)	ASTM D433
Specific Heat	745 - 958	J/(kg K)	DSC
ELECTRICAL PROPERTIES			
Dielectric Constant, 1 kHz	4.5 - 13.5	-	ASTM D150
Volume Resistivity, DC 68 °F, 65% R.H.	2E14	Ohm*cm	ASTM D257
Surface Resistivity, 73 °F	8.5E11 - 9.2E11	Ohm per square	ASTM D257
Dielectric (Electric) Strength, 73°F	0.8 - 1.1	kV/mil	ASTM D149

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SJC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

KYNAR SUPERFLEX®
BY ARKEMA

KYNAR SUPERFLEX® 2500-25

OTHER PROPERTIES			
Water Absorption	≤ 0.07	%	ASTM D570
Specific Gravity, 73 °F	1.8 - 1.82	-	ASTM D792

PROCESSING

Profile Extrusion, Other Extrusion

DELIVERY FORM

Pellets

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Kynar Superflex® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

kynar.com

KYNAR SUPERFLEX®

BY **ARKEMA**

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com