

LOTADER® AX8900

Ethylene – Acrylic Ester - Glycidyl Methacrylate terpolymer

DESCRIPTION

LOTADER® AX8900 is a random terpolymer of ethylene, acrylic ester and glycidyl methacrylate, polymerized by high-pressure autoclave process.

- Acrylic ester brings softness and polarity, while keeping high thermal stability during processing.
- The high content of acrylic ester leads to high flexibility (low cristallinity) and high impact absorption behaviour.
- Glycidyl methacrylate gives reactivity (versus OH, COOH and NH₂ groups), leading to optimal dispersion during melt mixing with engineering thermoplastics.
- As an ethylene copolymer, **LOTADER® AX8900** is compatible with LDPE in all proportions, and with almost all other ethylene copolymers.
- **LOTADER® AX8900** exhibits good adhesion on PET, PBT, PPS, metal, paper, and glass.

TYPICAL PROPERTIES

Characteristics	Value	Unit	Test Method
Methyl Acrylate content	24	%Wt	FTIR (internal method)
Glycidyl Methacrylate content	8	% Wt	FTIR (internal method)
Melt Index (190°C / 2.16 kg)	6	g/10min	ISO 1133 / ASTM D1238
Melting point	65	°C	ISO 11357-3
Density	0.94	g/cm ³	ISO 1183 / ASTM D1505
Vicat softening temperature (10N) ⁽¹⁾	<40	°C	ISO 306 / ASTM D1525
Flexural modulus ⁽¹⁾	<30	MPa	ISO 178 / ASTM D790
Elongation at break ⁽¹⁾	1100	%	ISO 527-2 / ASTM D638
Tensile strength at break ⁽¹⁾	4	MPa	ISO 527-2 / ASTM D638
Hardness Shore A/D (at 1s) ⁽¹⁾	64/18	-	ISO 868 / ASTM D2240

⁽¹⁾ On compression molded samples.

APPLICATIONS

Due to its properties, **LOTADER® AX8900** is suitable as additive (toughener) to improve the impact strength of engineering thermoplastics like polyesters (PBT, PET), PC/PBT and PC/ABS alloys, PPS. It can also be use as a compatibilizer for polyesters/polyolefins blends and in some formulated adhesive tapes. For more detailed information and recommendations regarding your specific application, please contact your local ARKEMA technical representative.

LOTADER®
BY ARKEMA

LOTADER® AX8900

Processing

Heat stability of acrylate comonomers allows processing temperatures as high as for polyesters (PBT, PET) and PPS, which are the main material using **LOTADER® AX8900** as impact modifier.

CAUTION: **LOTADER® AX8900** reacts with polymers containing maleic anhydride and acid. This reaction may generate gels or can block an extruder if not controlled. Extruders must be thoroughly purged before and after extruding **LOTADER® AX8900**.

STORAGE, HANDLING AND SAFETY

LOTADER® AX8900 should be stored in dry conditions and be kept out of moisture in an aerated building. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Due to its physical properties (Vicat temperature <40°C), it may be possible that the **LOTADER® AX8900** shows some caking. This is particularly true during summer time.

Safety data sheet as well as information on handling and storage of the **LOTADER® AX8900** is available upon request to your ARKEMA representative or on the web site lotader.com.

SHELF LIFE

Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

April 2014

The products described in the brochure are not Medical grades designated for Medical Device applications. Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications that are in contact with the body or circulating bodily fluids. Arkema has designated Medical grades to be used for such Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications that are in contact with the body or circulating bodily fluids. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See MSDS for Health & Safety Considerations

Arkema Functional Polyolefins
420, rue d'Estienne d'Orves
92705 Colombes Cedex - France
arkema.com – lotader.com

ARKEMA
INNOVATIVE CHEMISTRY