

LOTRYL® BESTPEEL 2407

Versatile heat seal resin for peelable applications

DESCRIPTION

LOTRYL® BESTPEEL 2407 is a ready-to-use thermoplastic composition designed to make peelable heat seal layers onto various substrates. The base resin is a random copolymer of ethylene and methyl acrylate, polymerized by high-pressure process in autoclave reactor. Modification is introduced to ensure the best processability in the different film technologies, and the suitable properties in heat sealing and peeling.

TYPICAL PROPERTIES

Characteristics	Value	Unit	Test Method
Methyl Acrylate content	23-25	% Wt	FTIR (Internal method)
Melt Index (190°C / 2.16 kg)	6-8	g/10min	ISO 1133 / ASTM D1238
Density (23°C)	0.94	g/cm ³	ISO 1183 / ASTM 1505
Melting point	69	°C	ISO 11357-3
Vicat softening point (10N) ⁽¹⁾	<40	°C	ISO 306 / ASTM D1525
Flexural modulus ⁽¹⁾	10	MPa	ISO 178 / ASTM D790
Elongation at break ⁽¹⁾	750	%	ISO 527-2 / ASTM D638
Tensile strength at break ⁽¹⁾	6	MPa	ISO 527-2 / ASTM D638
Hardness Shore A ⁽¹⁾	79	-	ISO 868 / ASTM D2240

⁽¹⁾ On compression molded samples.

APPLICATIONS

LOTRYL® BESTPEEL 2407 is used as top layer of laminates in order to provide the functions of *heat sealability* onto various substrates like PP, PS, PET and PVC, and *easy opening* by interfacial peeling.

LOTRYL® BESTPEEL 2407 is easily processed using the technologies of coextrusion coating, cast film coextrusion, blown film coextrusion or sheet coextrusion, to produce multilayers that can be used as lids, either directly or after lamination with other films. For more detailed information and recommendations regarding your specific application, please contact your local ARKEMA technical representative.

For more detailed information and recommendations regarding your specific application, please contact your local ARKEMA technical representative.

PROCESSING

LOTRYL® BESTPEEL 2407 is processed with standard polyolefin extrusion equipment. It is not corrosive and its processability is similar to that of LDPE. Temperatures can be chosen in a very wide range. Usual recommendations start from 170°C in blown film extrusion, up to 300 – 310 °C in extrusion coating, thanks to the excellent heat stability of acrylate comonomers.

The composition of **LOTRYL® BESTPEEL 2407** has been specifically designed to overcome the processing issues that are usually critical with tacky resins in film technologies, like chill roll release, blocking, bubble splitting and slip properties. **LOTRYL® BESTPEEL 2407** is proposed as a ready-to-use resin with outstanding processability at both extrusion and downstream stages.

Purging **LOTRYL® BESTPEEL 2407** is readily achieved with LDPE, and it is recommended to do it before shutdown.

HEAT SEALING AND PEELING PROPERTIES

LOTRYL® BESTPEEL 2407 can be used as peelable heat seal layer in many kinds of lid constructions, based on aluminium foil, plastic films, paper, or a combination of them.

LOTRYL®
BY ARKEMA

LOTRYL® BESTPEEL 2407

As examples of constructions:

- Aluminium foil / EAA or LOTADER 3210 / BESTPEEL 2407
- OPET / LOTADER 4503 / LDPE / BESTPEEL 2407
- OPET / PU adhesive / LDPE / BESTPEEL 2407
- Paper / LOTADER 4503 / PA6 / LOTADER 4503 / BESTPEEL 2407
- Paper / LOTADER 4503 / OPET / LOTADER 4503 / BESTPEEL 2407
- PA / OREVAC 18370 / PP / OREVAC 18370 / BESTPEEL 2407

Such constructions are heat sealable onto PP, PS, APET and PVC. Sealing strength is dependant on factors related to the different materials involved (heat conductivity, thicknesses) and to technological parameters like shape of the sealing tools, actual pressure, and time.

As general recommendations, flat sealing bars and moderate pressure should be preferred for better results and less squeezing of the sealing layer. Sealing temperature should be in the range from 160-180°C to 220-240°C, depending on heat conductivity of the whole structure and on contact time.

Example

<i>Lid construction:</i>	<i>Aluminium / tie / BESTPEEL 2407 (37 µm/6g/15g)</i>
<i>Conditions:</i>	<i>Flat sealing tool, 3 mm wide, 2.2 MPa actual pressure, 1s sealing time</i>
<i>Peeling initiation forces:</i>	<i>14 to 17 N/15mm with PS and PP, 12 N/15mm with APET and PVC</i>
<i>Peeling propagation forces:</i>	<i>5 N/3mm with PS and PP, 4 to 5 N/3mm with APET and PVC</i>

STORAGE, HANDLING, SAFETY AND FOOD STATUS

LOTRYL® BESTPEEL 2407 should be stored in standard conditions and protected from UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the **LOTRYL® BESTPEEL 2407** is available upon request to your ARKEMA representative or on the web site lotryl.com.

LOTRYL® BESTPEEL 2407 is compliant with the requirements of European and American regulations for use in food contact. Certificates are available upon request to your ARKEMA representative.

SHELF LIFE

Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

April 2014

The products described in the brochure are not Medical grades designated for Medical Device applications. Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications that are in contact with the body or circulating bodily fluids. Arkema has designated Medical grades to be used for such Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications that are in contact with the body or circulating bodily fluids. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See MSDS for Health & Safety Considerations.

Arkema Functional Polyolefins
420, rue d'Estienne d'Orves
92705 Colombes Cedex - France
arkema.com – lotryl.com

ARKEMA
INNOVATIVE CHEMISTRY