

OREVAC[®] 18732

Polypropylene based tie resin for pipe coating

DESCRIPTION

OREVAC[®] 18732 is a maleic anhydride modified polypropylene available in pellet form. It can be processed on most extrusion equipments designed to process conventional polyolefins.

TYPICAL PROPERTIES

Characteristics	Value	Unit	Test Method
Melt flow index (230°C / 2.16 kg)	8	g/10min	ISO 1133 / ASTM D1238
Density	0.89	g/cm ³	ISO 1183 / ASTM D1505
Melting Temperature	134	°C	ISO 11357-3
Vicat softening point (10N) ⁽¹⁾	120	°C	ISO 306 / ASTM D1525
Tensile strength at break ⁽¹⁾	20	MPa	ISO 527-2 / ASTM D638
Elongation at break ⁽¹⁾	500	%	ISO 527-2 / ASTM D638

⁽¹⁾ On compression molded samples

APPLICATIONS

OREVAC[®] 18732 is mainly used in applications where mechanical and adhesive performances at high temperatures are required. OREVAC[®] 18732 is used as tie layer in 3 layers polypropylene coatings (epoxy primer / adhesive / polypropylene) for external protection of steel pipe.

For more detailed information and recommendations regarding your specific application, please contact your local ARKEMA technical representative.

OREVAC® 18732

PROCESSING

OREVAC® 18732 is not corrosive and is readily processed with standard polyolefin equipment. Conditions typically used in extrusion of polypropylene resins are suitable.

Extrusion temperature settings could be:

Zone 1	Zone 2	Zone 3	Zone 4	Exit	Fittings-Channels	Die
160 - 180°C	180 - 200°C	200 - 220°C	210 - 230°C	215 - 230°C	220 - 230°C	220 - 240°C

Final profile and settings depend on the line.

STORAGE, HANDLING AND SAFETY

OREVAC® 18732 should be stored in dry conditions and protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of **OREVAC® 18732** is available upon request to your ARKEMA representative or at orevac.com

SHELF LIFE

Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

February 2014

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See MSDS for Health & Safety Considerations

Arkema Functional Polyolefins
 420, rue d'Estienne d'Orves
 92705 Colombes Cedex - France
arkema.com — orevac.com

ARKEMA
 INNOVATIVE CHEMISTRY