

OREVAC[®] CA100

Polypropylene based coupling agent

DESCRIPTION

OREVAC[®] CA100 is a chemically functionalized polypropylene with a high content of maleic anhydride. Grafted maleic anhydride induces polarity to polypropylene and so outstanding adhesion properties on glass and natural fibers, and mineral fillers.

TYPICAL PROPERTIES

Characteristics	Value	Unit	Test Method
Melt index (190°C / 0.325 kg)	10	g/10min	ISO 1133 / ASTM D1238
Melting point	167	°C	ISO 11357-3
Density	0.905	g/cm ³	ISO 1183 / ASTM D1505
Vicat softening temperature (10N) ⁽¹⁾	147	°C	ISO 306 / ASTM D1525
Flexural modulus ⁽¹⁾	880	MPa	ISO 178 / ASTM D790
Strength at yield ⁽¹⁾	22	MPa	ISO 527-2 / ASTM D638
Strength at break ⁽¹⁾	22	MPa	ISO 527-2 / ASTM D638
Elongation at break ⁽¹⁾	12	%	ISO 527-2 / ASTM D638

⁽¹⁾ On compression molded samples

APPLICATIONS

OREVAC[®] CA100 has been designed as coupling agent to develop a reliable bonding strength between PP or PA resins and glass fiber, mineral filler or natural fibers.

For more detailed information and recommendations regarding your specific application, please contact your local ARKEMA technical representative.

OREVAC® CA100

PROCESSING

OREVAC® CA100 can be processed over a wide range of conditions. Compounding can be achieved on conventional equipments such as mono-screw, twin-screw or co-kneader with usual temperatures.

STORAGE, HANDLING AND SAFETY

OREVAC® CA100 should be stored in dry conditions protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of **OREVAC® CA100** is available upon request to your ARKEMA representative or at orevac.com

SHELF LIFE

Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

April 2014

The products described in the brochure are not Medical grades designated for Medical Device applications. Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications that are in contact with the body or circulating bodily fluids. Arkema has designated Medical grades to be used for such Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications that are in contact with the body or circulating bodily fluids. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See MSDS for Health & Safety Considerations.

Arkema Functional Polyolefins
420, rue d'Estienne d'Orves
92705 Colombes Cedex - France
arkema.com — orevac.com

ARKEMA
INNOVATIVE CHEMISTRY