

ORGALLOY® LE 6000 ST NAT

Orgalloy® LE 6000 ST NAT resin is a polyamide alloy especially designed for blown film extrusion and cable sheathing. This natural grade dedicated to extrusion offers excellent barrier properties and chemical resistance to hydrocarbons, alcohols and solvents.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	2 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
Load	2.16 / *	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 1400	MPa	ISO 527-1/-2
Yield stress	- / 36	MPa	ISO 527-1/-2
Yield strain	- / 7	%	ISO 527-1/-2
Nominal Strain at Break	- / > 50	%	ISO 527-1/-2
Shore D Hardness, 15s	66 / *	-	ISO 7619-1
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 35	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 15	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
Vicat Softening Temperature, 50°C/h 50N	118 / *	°C	ISO 306
OTHER PROPERTIES			
Water Absorption	0.8 / *	%	Sim. to ISO 62
Density	1040 / 1040	kg/m ³	ISO 1183

MAIN APPLICATIONS:

- Technical films for Bulk Molding Compound (BMC)
- Inner liner for octabin containing Expanded PolyStyrene (EPS)

PACKAGING:

This grade is delivered dried in sealed packaging (800kg octabin) ready to be processed.

SHELF LIFE:

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Drying time (only necessary for bags opened for more than two hours): 4-8 hours at 80°C
- Extrusion melt temperature (min-recommended-max): 250-260-270°C

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

ORGALLOY®
BY **ARKEMA**

ORGALLOY® LE 6000 ST NAT

PROCESSING

Film Extrusion, Other Extrusion

DELIVERY FORM

Pellets

ADDITIVES

Lubricants

SPECIAL CHARACTERISTICS

Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Orgalloy® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

orgalloy.com

ORGALLOY®
BY ARKEMA

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com