

ORGALLOY® RS 6600 BLACK

Orgalloy® RS 6600 BLACK resin is a polyamide 66 alloy designed for injection molding. This black grade offers an outstanding dimensional stability, chemical resistance to automotive fluids and is ideal for the realization of complex parts.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	24 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	2.16 / *	kg	-
Molding Shrinkage, parallel	0.5 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.1 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	2330 / 2200	MPa	ISO 527-1/-2
Yield stress	55 / 52	MPa	ISO 527-1/-2
Yield strain	6 / 10	%	ISO 527-1/-2
Nominal Strain at Break	15 / 20	%	ISO 527-1/-2
Shore D Hardness, 15s	76 / *	-	ISO 7619-1
Tensile Creep Modulus, 1h	* / 2300	MPa	ISO 899-1
Tensile Creep Modulus, 1000h	* / 980	MPa	ISO 899-1
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	7 / 8	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	255 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	80 / *	°C	ISO 75-1/-2
Temp. of Deflection Under Load, 0.45 MPa	160 / *	°C	ISO 75-1/-2
Vicat Softening Temperature, 50°C/h 50N	170 / *	°C	ISO 306
Coeff. of Linear Thermal Expansion, parallel	65 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Thermal Expansion, normal	110 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nominal Thickness	HB / *	class	IEC 60695-11-10
Thickness Tested	1.6 / *	mm	-
Yellow Card available	yes / *	-	-
Burning Behav. at Thickness h	HB / *	class	IEC 60695-11-10
Thickness Tested	3.2 / *	mm	-
Yellow Card available	yes / *	-	-
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	- / 3	-	IEC 60250
Relative Permittivity, 1MHz	- / 3	-	IEC 60250
Dissipation Factor, 100Hz	- / 250	E-4	IEC 60250

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

ORGALLOY®
BY ARKEMA

ORGALLOY® RS 6600 BLACK

Dissipation Factor, 1MHz	- / 170	E-4	IEC 60250
Volume Resistivity	- / > 1E13	Ohm*m	IEC 60093
Surface Resistivity	* / > 1E15	Ohm	IEC 60093
Dielectric (Electric) Strength	36 / 36	kV/mm	IEC 60243-1
Comparative Tracking Index	* / 600	-	IEC 60112
OTHER PROPERTIES			
Water Absorption	2.9 / *	%	Sim. to ISO 62
Humidity Absorption	1.2 / *	%	Sim. to ISO 62
Density	1040 / 1040	kg/m ³	ISO 1183

MAIN APPLICATIONS: • Electric connectors • Sport parts • Automotive fan shrouds

PACKAGING:


This grade is delivered dried in sealed packaging (25kg bags) ready to be processed.

SHELF LIFE:


Two years from the date of delivery. For any use above this limit, please refer to our technical services.

DIAGRAMS

VISCOSITY-SHEAR RATE




SHEARSTRESS-SHEAR RATE




ORGALLOY® RS 6600 BLACK


DYNAMIC SHEAR MODULUS-TEMPERATURE




STRESS-STRAIN



SECANT MODULUS-STRAIN



SPECIFIC VOLUME-TEMPERATURE (PVT)



Processing conditions:

- Drying time (only necessary for bags opened for more than two hours): 4-8 hours at 80°C
- Injection temperature (min-recommended-max): 260-270-280°C
- Mould temperature (min-max): 60-80°C

PROCESSING

Injection Molding

SPECIAL CHARACTERISTICS

Heat Stabilized, Light Stabilized

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

ORGALLOY®
BY ARKEMA

ORGALLOY® RS 6600 BLACK

DELIVERY FORM

Pellets

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Orgalloy® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

orgalloy.com

ORGALLOY®
BY **ARKEMA**

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com