

PEBAX® 6333 SA 01 MED

Polyether block amide **Pebax® 6333 SA 01 MED resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices.

Pebax® 6333 SA 01 MED resin also offers an excellent combination of properties such as: kink resistance, low friction coefficient and superior dynamic response.

Upon request, letters regarding USP Class VI compliance can be provided.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Molding Shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.4 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	307 / 285	MPa	ISO 527-1/-2
Yield stress	19 / 18	MPa	ISO 527-1/-2
Yield strain	22 / 22	%	ISO 527-1/-2
Nominal Strain at Break	>50 / >50	%	ISO 527-1/-2
Shore D Hardness, 15s	58 / *	-	ISO 7619-1
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 20	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	169 / *	°C	ISO 11357-1/-3
Vicat Softening Temperature, 50°C/h 50N	157 / *	°C	ISO 306
OTHER PROPERTIES			
Water Absorption	1.1 / *	%	Sim. to ISO 62
Humidity Absorption	0.7 / *	%	Sim. to ISO 62
Density	1010 / -	kg/m ³	ISO 1183

MAIN APPLICATIONS: • Tubings like angiography and angioplasty catheters • Flexible injected parts

PACKAGING:

This grade is delivered dried in sealed packaging (20 kg bags) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PEBAX®
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

PEBAX® 6333 SA 01 MED

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 260°C / 290°C.
- Typical mold temperature : 25 – 60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 65-75°C.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 210°C / 225°C / 240°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 65-75°C.

PROCESSING

Injection Molding, Other Extrusion

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Heat Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

[pebax.com](https://www.pebax.com)

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
[arkema-america.com](https://www.arkema-america.com)

PEBAX®
BY **ARKEMA**

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
[arkema.com](https://www.arkema.com)