

PEBAX® CLEAR 1200

Pebax® Clear 1200 resin combines a high transparency level with the excellent performance of Pebax® thermoplastic elastomer resin.

Pebax® Clear 1200 resin is produced from a renewable source.

The percentage of **renewable carbon is 90%** (calculated value, based on ASTM D6866).

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Molding Shrinkage, parallel	1.0 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.1 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	- / 1300	MPa	ISO 527-1/-2
Yield stress	- / 43	MPa	ISO 527-1/-2
Yield strain	- / 5.1	%	ISO 527-1/-2
Nominal Strain at Break	- / > 50	%	ISO 527-1/-2
Shore D Hardness, 15s	73 / *	-	ISO 7619-1
Charpy Notched Impact Strength, +23°C	- / 8	kJ/m²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 12	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	180 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1030 / -	kg/m³	ISO 1183
%Bio-Based	90	-	ASTM D6866
OPTICAL PROPERTIES			
Luminous Transmittance	80	%	ISO 13468-1, -2

MAIN APPLICATIONS: • Consumer goods • Sports equipment

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags).

SHELF LIFE:

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 250°C / 270°C / 290°C.
- Typical mold temperature (mirror polish to get the optimum transparency) : 50–70°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80°C.

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PEBAX®
CLEAR
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

PEBAX® CLEAR 1200

PROCESSING

Injection Molding

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Bio-Based, Transparent

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

pebax.com

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

PEBAX®
CLEAR
BY **ARKEMA**

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com