

PEBAX® MH 2030

Polyether block amide **Pebax® MH 2030 resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide.
Pebax® MH 2030 resin is an inherently dissipative polymer and can be dry blended or compounded with an isolative polymer to lower the surface resistivity of the final part.

Refractive index according to an internal method is 1.508.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	- / 80	MPa	ISO 527-1/-2
Shore D Hardness, 15s	40 / *	-	ISO 7619-1
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	200 / *	°C	ISO 11357-1/-3
ELECTRICAL PROPERTIES			
Volume Resistivity	- / 100000	Ohm*m	IEC 60093
Surface Resistivity	* / 1E7	Ohm	IEC 60093
OTHER PROPERTIES			
Water Absorption	120 / *	%	Sim. to ISO 62
Humidity Absorption	4.5 / *	%	Sim. to ISO 62
Density	1140 / 1140	kg/m³	ISO 1183

MAIN APPLICATIONS:

- Permanent antistatic additive

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 230°C / 240°C / 260°C.
- Typical mold temperature: 25–60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 5-7 hours at 70-90°C.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 230°C / 250°C / 280°C
- Drying time and temperature (only necessary for bags opened for more than two hours): 5-7 hours at 70-90°C

PROCESSING

Injection Molding, Other Extrusion

SPECIAL CHARACTERISTICS

Anti-Static

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PEBAX®
 BY ARKEMA

PEBAX® MH 2030

DELIVERY FORM

Pellets

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

[pebax.com](https://www.pebax.com)

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
[arkema-america.com](https://www.arkema-america.com)

PEBAX®
BY **ARKEMA**

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
[arkema.com](https://www.arkema.com)