

PEBAX® MV 1074 SA 01

Polyether block amide **Pebax® MV 1074 SA 01 resin** is a thermoplastic elastomer made of flexible and hydrophilic polyether and rigid polyamide.

Pebax® MV 1074 SA 01 resin is also an inherently dissipative polymer and can be dry blended or compounded with a polymer matrix to lower the surface resistivity of the final part.

This hydrophilic grade when extruded into either a thin film or laminated on to a substrate offers excellent permeability to moisture vapor while remaining waterproof .

This SA grade is specially designed to food uses.

Refractive index according to an internal method is 1.502.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	97 / 80	MPa	ISO 527-1/-2
Stress at 50% Strain	10 / 10	MPa	ISO 527-1/-2
Strain at Break	> 50 / > 50	%	ISO 527-1/-2
Strain at Break TPE	> 300 / *	%	ISO 527-1/-2
Stress at Break TPE	30 / *	MPa	ISO 527-1/-2
Shore D Hardness, 15s	40 / *	-	ISO 7619-1
Charpy Impact Strength, +23°C	No Break / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	No Break / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	No Break / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	No Break / -	kJ/m ²	ISO 179/1eA
Maximum Stress, parallel	32 / *	MPa	ISO 527-3
Maximum Stress, normal	34 / *	MPa	ISO 527-3
Maximum Strain, parallel	500 / *	%	ISO 527-3
Maximum Strain, normal	700 / *	%	ISO 527-3
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	158 / *	°C	ISO 11357-1/-3
Glass Transition Temperature, 10°C/min	-40 / *	°C	ISO 11357-1/-2
Oxygen Index	19 / *	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Volume Resistivity	1.5E9 / 2.5E7	Ohm*m	IEC 60093
Surface Resistivity	* / 3E9	Ohm	IEC 60093
Dielectric (Electric) Strength	5 / -	kV/mm	IEC 60243-1
OTHER PROPERTIES			
Humidity Absorption	1.4 / *	%	Sim. to ISO 62
Density	1070 / -	kg/m ³	ISO 1183

MAIN APPLICATIONS:

- reathable membranes
- Permanent antistatic additive
- Note: this grade is not recommended by Arkema for usage in medical

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PEBAX®
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

PEBAX® MV 1074 SA 01

Pebax® SA 01 MED should be used

applications. For such applications

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags and 550 kg rigid containers) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 200°C / 240°C / 270°C.
- Typical mold temperature: 25–60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 210°C / 220°C / 230°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

PROCESSING

Injection Molding, Other Extrusion

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Anti-Static, Heat Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

pebax.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

PEBAX®
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com