

PEBAX® MV 3000 SP 01

Polyether block **Pebax® MV 3000 SP 01 resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This hydrophilic grade when extruded into either a thin film or laminated on to a substrate offers excellent permeability to moisture vapor while remaining waterproof.

This SP grade is specifically designed for outdoor application that needs excellent weather resistance properties.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	- / 45	MPa	ISO 527-1/-2
Stress at 50% Strain	- / 7	MPa	ISO 527-1/-2
Strain at Break	- / > 50	%	ISO 527-1/-2
Shore D Hardness, 15s	35 / *	-	ISO 7619-1
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	158 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Water Absorption	28 / *	%	Sim. to ISO 62
Humidity Absorption	1 / *	%	Sim. to ISO 62
Density	1020 / 1020	kg/m ³	ISO 1183

MAIN APPLICATIONS:

- Breathable membranes

PACKAGING:

This grade is delivered dried in sealed packaging (20 kg bags) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Cast Film - Typical melt temperature : 240 - 250°C.
- Blown Film - Typical melt temperature : 190 - 210°C.
- Coating - Typical melt temperature : 240 - 250°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 70-80°C.

PROCESSING

Film Extrusion, Other Extrusion, Calendering, Casting

DELIVERY FORM

Pellets

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PEBAX®
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

PEBAX® MV 3000 SP 01



Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

pebax.com

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

PEBAX®
BY ARKEMA

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com