

PEBAX® RNEW® 63R53 SP 01

Polyether block **Pebax® Rnew® 63R53 SP 01 resin** is a thermoplastic elastomer made of flexible polyether and rigid polyamide based on renewable resources. This SP grade has been developed to be heat and UV resistant.

The percentage of **renewable carbon measured** according to ASTM D6866 is 77%.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Molding Shrinkage, parallel	1.3 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.2 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	- / 245	MPa	ISO 527-1/-2
Yield stress	- / 19	MPa	ISO 527-1/-2
Yield strain	- / 40	%	ISO 527-1/-2
Nominal Strain at Break	- / > 50	%	ISO 527-1/-2
Strain at Break TPE	> 300 / *	%	ISO 527-1/-2
Stress at Break TPE	51 / *	MPa	ISO 527-1/-2
Shore D Hardness, 15s	56 / *	-	ISO 7619-1
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 22	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	180 / *	°C	ISO 11357-1/-3
Vicat Softening Temperature, 50°C/h 50N	168 / *	°C	ISO 306
OTHER PROPERTIES			
Water Absorption	1.5 / *	%	Sim. to ISO 62
Humidity Absorption	0.8 / *	%	Sim. to ISO 62
Density	1030 / 1030	kg/m ³	ISO 1183
%Bio-Based	77	-	ASTM D6866

MAIN APPLICATIONS:

- Ski shoes
- Athletic foot wear components

PACKAGING:

This grade is delivered dried in sealed packaging (20 and 25 kg bags) ready to be processed.

SHELF LIFE:

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>


PEBAX®
RNEW
BY ARKEMA

PEBAX® RNEW® 63R53 SP 01


Two years from the delivery. For any use above this limit, please refer to our technical services.

DIAGRAMS

STRESS-STRAIN



SECANT MODULUS-STRAIN



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 260°C / 290°C
- Typical mold temperature : 25 – 60°C
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 65-75°C

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 210°C / 225°C / 240°C
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-8 hours at 65-75°C

PROCESSING

Injection Molding, Film Extrusion, Profile Extrusion, Other Extrusion, Transfer Molding, Casting, Thermoforming

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Bio-Based, Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® Rnew® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

pebax.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

PEBAX®
RNEW
BY **ARKEMA**

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018