

PLATAMID® H 106 POWDER

Platamid® H 106 Powder

Copolyamide Hot Melt Adhesive / Textile Applications

Platamid® H 106 Powder is a very low melt copolyamide adhesive powder for the production of fusible interlinings. **Platamid® H 106 Powder** is particularly useful where bonding temperature low and short bonding time are required for sensitive shell fabrics.

Platamid® H 106 Powder has an excellent dry cleaning resistance and washing resistance up to 40°C.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	90 / *	cm ³ /10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	115 / *	°C	ISO 11357-1/-3

AVAILABLE GRADES

This product is available in different grain sizes:

- Platamid® H 106 PA 100
- Platamid® H 106 PA 80 (0-80 µm)
- Platamid® H 106 PRA 200/25 (0-200 µm)
- Platamid® H 106 PTA 120 (0-120 µm)
- Platamid® H 106 PTA 170 (80-170 µm)
- Platamid® H 106 PTA 170/20 (0-70 µm)
- Platamid® H 106 PA 80 Black
- Platamid® H 106 PA 80 Red
- Platamid® H 106 PRA 170
- Platamid® H 106 PTA 170 Black
- Platamid® H 106 PTA 170 Red
- Platamid® H 106 PTA 60/150

PACKAGING

All grades are delivered in 20 kg sealed bags.

Platamid® H 106 PA 80 is also delivered in 500 kg sealed big bags (GRVS).

These grades are ready to be processed.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

DELIVERY FORM

Powder

SPECIAL CHARACTERISTICS

Adhesive

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PLATAMID®
BY **ARKEMA**

PLATAMID[®] H 106 POWDER



Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid[®] is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

platamid.com

PLATAMID[®]
BY ARKEMA

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com