

PLATAMID® H 2513 PELLETS

Platamid® H 2513 Pellets

Copolyamide Hot Melt Adhesive

Platamid® H 2513 is a standard thermoplastic copolyamide hot melt adhesive available in pellet form. This low to medium melt viscosity, fast re-crystallizing grade is particularly suitable for manufacturing webs, nets, mono- and multi-filaments, and films by extrusion.

Platamid® H 2513 offers a very good adhesion to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc).

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	26 / *	cm ³ /10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	128 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1070 / -	kg/m ³	ISO 1183

AVAILABLE GRADES

This grade is available dried with optical brightener (Platamid® H 2513 TA)

PACKAGING

Platamid® H 2513 is delivered in 25 kg sealed bags and 500 kg sealed big bags (GRVS).

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Adhesive

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

platamid.com

PLATAMID®
BY ARKEMA

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018