

PLATAMID® H 2519 PELLETS

Platamid® H 2519 Pellets

Copolyamide Hot Melt Adhesive / Extrusion Applications

Platamid® H 2519 is a thermoplastic co-polyamide hot melt adhesive available in pellet form. This medium melt viscosity, fast re-crystallizing grade is particularly suitable for manufacturing webs, nets, mono- and multi-filaments, and films by extrusion.

Platamid® H 2519 offers a very good adhesion to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc). In addition, **Platamid® H 2519** also exhibits strong adhesion onto rigid and plasticized PVC as well as ABS, epoxy resin, PU, etc. Dense layers of **Platamid® H 2519** are known to have barrier properties against PVC plasticizer migration.

Platamid® H 2519 is also characterized by a high content of Bio Based Carbon, making it a bio based solution to difficult-to-solve bonding problems.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	8 / *	cm ³ /10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
OTHER PROPERTIES			
Density	1090 / -	kg/m ³	ISO 1183
%Bio-Based	50	-	ASTM D6866

AVAILABLE GRADES

This product is available:

- Dried (H 2519 T)
- Un-dried (H 2519 F)

PACKAGING

- Platamid® H 2519 T is delivered in 25 kg sealed bags.
 - Platamid® H 2519 F is delivered in 25 kg sealed bags, 500 kg sealed big bags (GRVS or GRVS ALU) and 500 kg sealed rigid containers (GRVC).
- These grades are ready to be processed.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON CONTENT

50% (calculated, ASTM D6866)

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Adhesive, Bio-Based

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

PLATAMID[®] H 2519 PELLETS



Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid[®] is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

platamid.com

PLATAMID[®]
BY ARKEMA

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com