

PLATAMID® H 2707 PELLETS

Platamid® H 2707 Pellets

Copolyamide Hot Melt Adhesive / Extrusion Applications

Platamid® H 2707 is a standard thermoplastic copolyamide hot melt adhesive available in pellet form. This medium to high melt viscosity grade is particularly suitable for manufacturing webs, mono- and multi-filaments, and films by extrusion.

Platamid® H 2707 offers a good adhesion at low fusing conditions to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc.).

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	2 / *	cm ³ /10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	102 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1060 / -	kg/m ³	ISO 1183

AVAILABLE GRADES

This grade is available:

- dried (H 2707 T)

PACKAGING

- Platamid® H 2707 T is delivered in 25 kg sealed bags.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON CONTENT

20% (calculated)

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Adhesive, Bio-Based

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

platamid.com

PLATAMID®
BY **ARKEMA**

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com