

PLATAMID® HX 2667 POWDER

Platamid® HX 2667 Powder

Copolyamide Hot Melt Adhesive / Textile Applications

Platamid® HX 2667 Powder is a medium melt viscosity copolyamide adhesive powder for the production of fusible interlinings.

Platamid® HX 2667 Powder offers excellent laundry resistance up to 60°C and an excellent resistance to all kind of steam treatment.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	30 / *	cm³/10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	128 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
%Bio-Based	60	-	ASTM D6866

AVAILABLE GRADES

This grade is available in different grain sizes:

- Platamid® HX 2667 PA80 (0-80 µm paste dot)
- Platamid® HX 2667 PTA 170/20 (0-170 µm power dot)
- Platamid® HX 2667 PTA 170 (80-170 µm double dot)

PACKAGING

- Platamid® HX 2667 PA80 and Platamid® HX 2667 PTA 170/20 are delivered in 20 kg sealed bags.
- Platamid® HX 2667 PTA 170 is delivered in 20 kg sealed bags.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON CONTENT

60% (calculated, ASTM D6866)

DELIVERY FORM

Powder

SPECIAL CHARACTERISTICS

Adhesive, Bio-Based

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

platamid.com

PLATAMID®
BY ARKEMA

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com