

PLATAMID® M 1276 PELLETS

Platamid® M 1276 Pellets

Copolyamide Hot Melt Adhesive / Extrusion Applications

Platamid® M 1276 is a thermoplastic co-polyamide hot melt adhesive available in pellet form. This medium melt viscosity grade is particularly suitable for manufacturing webs, nets, mono- and multi-filaments, and films by extrusion.

Platamid® M 1276 offers a very good adhesion to various polar substrates (thermoplastics, thermosets, metal natural fibers, etc). In addition, **Platamid® M 1276** also exhibits strong adhesion onto rigid and plasticized PVC as well as ABS, epoxy resin, PU etc. Dense layers of **Platamid® M 1276** are known to have barrier properties against PVC plasticizer migration.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	6 / *	cm ³ /10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	110 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1100 / -	kg/m ³	ISO 1183
%Bio-Based	26	-	ASTM D6866

AVAILABLE GRADES

This product is available:

- Dried (M 1276 TE)
- Un-dried (M 1276 F)

PACKAGING

- Platamid® M 1276 TE is delivered in 25 kg sealed bags.
 - Platamid® M 1276 F is delivered in 25 kg sealed bags and 500 kg sealed big bags (GRVS).
- These grades are ready to be processed.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON:

26% (calculated, ASTM D6866)

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Adhesive, Bio-Based

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PLATAMID®
BY **ARKEMA**

PLATAMID[®] M 1276 PELLETS



Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid[®] is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

[platamid.com](https://www.platamid.com)

PLATAMID[®]
BY ARKEMA

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
[arkema-america.com](https://www.arkema-america.com)

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
[arkema.com](https://www.arkema.com)