

PLATAMID® M 1757 PELLETS

Platamid® M 1757 Pellets

Copolyamide Hot Melt Adhesive / Extrusion Applications

Platamid® M 1757 is a standard thermoplastic co-polyamide hot melt adhesive available in pellet form. This low to medium melt viscosity, fast re-crystallizing grade is particularly suitable for manufacturing webs, nets, mono- and multi-filaments, and films by extrusion.

Platamid® M 1757 offers a very good adhesion to various polar substrates (thermoplastics, thermosets, metal natural fibers, etc).

Platamid® M 1757 has a very good dry cleaning resistance and washing resistance up to 60°C.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	27 / *	cm ³ /10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	106 / *	°C	ISO 11357-1/-3

AVAILABLE GRADES

This product is available:

- Dried with optical brightener (M 1757 TA)
- Un-dried with optical brightener (M 1757 FA)

PACKAGING

- Platamid® M 1757 TA is delivered in 25 kg sealed bags.
- Platamid® M 1757 FA is delivered in 500 kg sealed big bags (GRVS).

These grades are ready to be processed.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Adhesive

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

platamid.com

PLATAMID®
BY **ARKEMA**

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com