

PLATAMID® M 2468 PELLETS

Platamid® M 2468 Pellets

Copolyamide Hot Melt Adhesive / Extrusion Applications

Platamid® M 2468 is a standard thermoplastic copolyamide hot melt adhesive available in pellet form. This low to medium melt viscosity grade is particularly suitable for manufacturing webs, nets, mono- and multi-filaments, and films by extrusion.

Platamid® M 2468 offers a good adhesion at low fusing conditions to various polar substrates (thermoplastics, thermosets, metal, natural fibers, etc).

Platamid® M 2468 has good dry cleaning resistance and washing resistance up to 60°C.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	26 / *	cm ³ /10min	ISO 1133
Temperature	160 / *	°C	-
Load	2.16 / *	kg	-
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	102 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1060 / -	kg/m ³	ISO 1183
%Bio-Based	25	-	ASTM D6866

AVAILABLE GRADES

This product is available:

- Dried with optical brightener (M 2468 TA)
- Un-dried with optical brightener (M 2468 FA)

PACKAGING

- Platamid® M 2468 TA is delivered in 25 kg sealed bags and 500kg sealed big bags (GRVS).
 - Platamid® M 2468 FA is delivered in 500kg sealed rigid containers (GRVC) and 500kg sealed big bags (GRVS).
- These grades are ready to be processed.

SHELF LIFE

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

RENEWABLE CARBON CONTENT

>25% (calculated, ASTM D6866)

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Adhesive, Bio-Based

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Platamid® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

platamid.com

PLATAMID®
BY **ARKEMA**

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018