

RILSAMID® AESN BLACK P201 TL

ISO 16396 - PA12-HIP, EGHL, C22-007

Rilsamid® AESN BLACK P201 TL resin is a black colored polyamide 12.

This grade is plasticized and designed for tube extrusion.

Rilsamid® AESN BLACK P201 TL resin falls into the PA12-PHLY category according to DIN 73378.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	5 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
Load	5 / *	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 540	MPa	ISO 527-1/-2
Yield stress	- / 30	MPa	ISO 527-1/-2
Yield strain	- / 22	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, 15s	64 / *	-	ISO 7619-1
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 7	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	176 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1010 / 1010	kg/m ³	ISO 1183

MAIN APPLICATIONS:

- Air brake
- Tubing for use in motor vehicles

PACAKAGING:

This material is delivered in sealed packaging (800 kg rigid containers) ready to be processed.

SHELF LIFE:

Two years from date of delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature: (Min / Recommended / Max): 230°C / 250 °C / 270 °C
- Drying time and temperature (only necessary if containers opened for more than two hours): 4 - 6 hours at 80°C

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

RILSAMID®
BY **ARKEMA**

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SJC/11-2018

RILSAMID® AESN BLACK P201 TL

PROCESSING

Profile Extrusion, Other Extrusion

DELIVERY FORM

Pellets

ADDITIVES

Lubricants, Plasticizer

SPECIAL CHARACTERISTICS

Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsamid® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsamid.com

RILSAMID®
BY ARKEMA

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com