

RILSAMID® AZM 50 BLACK T6LD

ISO 16396 - PA12, GF50, M1GHLR, C16-120

Rilsamid® AZM 50 BLACK T6LD resin is a fiberglass reinforced polyamide. This black colored grade is designed for injection molding.

(The values came from studies 2019-1100 & 2020-0626)

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	6 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
Load	5 / *	kg	-
Molding Shrinkage, parallel	0.1 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	0.7 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	12000 / 12100	MPa	ISO 527-1/-2
Yield stress	153 / 145	MPa	ISO 527-1/-2
Yield strain	3.8 / 3.6	%	ISO 527-1/-2
Nominal Strain at Break	4.4 / 4.6	%	ISO 527-1/-2
Stress at Break	152 / 144	MPa	ISO 527-1/-2
Strain at Break	4.6 / 4.9	%	ISO 527-1/-2
Charpy Impact Strength, +23°C	84 / 80	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	90 / 84	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	22 / 21	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	15 / 15	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	175 / *	°C	ISO 11357-1/-3
Thermal Decomposition TGA, in air	224	°C	1% wt. loss
Thermal Decomposition TGA, in nitrogen	224	°C	1% wt. loss
OTHER PROPERTIES			
Density	1.47 / -	kg/m ³	ISO 1183

PACKAGING :&NBSP;

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed

SHELF LIFE :

Two years from the delivery.

For any use above this limit please refer to our technical services.

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

RILSAMID®
BY **ARKEMA**

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

RILSAMID® AZM 50 BLACK T6LD

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 250°C / 265°C / 280°C.
- Typical mold temperature : 40 – 90°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

PROCESSING

Injection Molding

DELIVERY FORM

Granules

ADDITIVES

Release agent

SPECIAL CHARACTERISTICS

Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsamid® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsamid.com

RILSAMID®
BY ARKEMA

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com