

RILSAN® BESN BLACK P123 TL

PA11, EHLN, 22-010

Rilsan® BESN BLACK P123 TL resin is a flexible polyamide 11 produced from a renewable source. This black grade is designed for extrusion typically for cooling application and for Adblue circuits (SCR).

The pourcentage of renewable carbon (calculated) is 67% (Value obtained from **a calculation** based on the composition of the raw material that are used to manufacture the product. Arkema has not made a specific measure on the product).

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Yield stress	- / 25	MPa	ISO 527-1/-2
Yield strain	- / 33	%	ISO 527-1/-2
Nominal Strain at Break	- / > 50	%	ISO 527-1/-2
Charpy Notched Impact Strength, +23°C	- / 100	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 25	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	189 / *	°C	ISO 11357-1/-3
OTHER PROPERTIES			
Density	1000 / 1000	kg/m ³	ISO 1183
%Bio-Based	67	-	ASTM D6866

MAIN APPLICATIONS:

- Cooling application
- Adblue circuits (SCR)

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 260°C / 275°C / 290°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

PROCESSING

Profile Extrusion, Other Extrusion, Blow Molding

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Bio-Based, Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsan.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

RILSAN®
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018