

RILSAN® BESN BLACK P20 TL

PA11-P,E HL, 22-005

Rilsan® BESN BLACK P20 TL resin is a polyamide 11 produced from a renewable source. This black grade is plasticized and designed for extrusion.

The percentage of renewable carbon according to ASTM D 6866 (calculated) is **>92%**.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	- / 560	MPa	ISO 527-1/-2
Yield stress	- / 32	MPa	ISO 527-1/-2
Yield strain	- / 33	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 70	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 10	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	182 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	47 / *	°C	ISO 75-1/-2
Temp. of Deflection Under Load, 0.45 MPa	135 / *	°C	ISO 75-1/-2
OTHER PROPERTIES			
Water Absorption	1.8 / *	%	Sim. to ISO 62
Density	1040 / 1040	kg/m ³	ISO 1183
%Bio-Based	92	-	ASTM D6866

MAIN APPLICATIONS:

- Fluid transportation
- Tubing for use in motor vehicle

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags / 550 kg rigid containers) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 280°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 80-90°C.

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

RILSAN®
BY **ARKEMA**

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SJC/11-2018

RILSAN® BESN BLACK P20 TL

PROCESSING

Profile Extrusion, Other Extrusion

DELIVERY FORM

Pellets

ADDITIVES

Lubricants, Plasticizer

SPECIAL CHARACTERISTICS

Bio-Based, Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsan.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

RILSAN®
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com