

RILSAN® BESNO P40 TL

PA11-P, EHL, 22-003

Rilsan® BESNO P40 TL resin is a polyamide 11 produced from a renewable source. This natural grade is plasticized and designed for extrusion.

The percentage of renewable carbon according to ASTM D 6866 (calculated) is **>89%**.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	3 / *	cm³/10min	ISO 1133
Temperature	235 / *	°C	-
Load	10 / *	kg	-
MECHANICAL PROPERTIES			
Tensile Modulus	- / 345	MPa	ISO 527-1/-2
Yield stress	- / 26	MPa	ISO 527-1/-2
Yield strain	- / 50	%	ISO 527-1/-2
Nominal Strain at Break	- / > 50	%	ISO 527-1/-2
Shore D Hardness, 15s	60 / *	-	ISO 7619-1
Charpy Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / No Break	kJ/m²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	- / 7	kJ/m²	ISO 179/1eA
Puncture - Maximum Force, -30°C	- / 6000	N	ISO 6603-2
Puncture Energy, -30°C	- / 70	J	ISO 6603-2
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	181 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	45 / *	°C	ISO 75-1/-2
Temp. of Deflection Under Load, 0.45 MPa	130 / *	°C	ISO 75-1/-2
Vicat Softening Temperature, 50°C/h 50N	140 / *	°C	ISO 306
Coeff. of Linear Thermal Expansion, parallel	110 / *	E-6/K	ISO 11359-1/-2
ELECTRICAL PROPERTIES			
Relative Permittivity, 100Hz	9 / -	-	IEC 60250
Relative Permittivity, 1MHz	4 / -	-	IEC 60250
Dissipation Factor, 100Hz	2440 / -	E-4	IEC 60250
Dissipation Factor, 1MHz	1040 / -	E-4	IEC 60250
Volume Resistivity	- / 1E9	Ohm*m	IEC 60093
Surface Resistivity	* / 5E11	Ohm	IEC 60093

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

RILSAN®
BY ARKEMA

RILSAN® BESNO P40 TL

Dielectric (Electric) Strength	- / 23	kV/mm	IEC 60243-1
OTHER PROPERTIES			
Water Absorption	1.6 / *	%	Sim. to ISO 62
Density	1040 / 1040	kg/m ³	ISO 1183
%Bio-Based	89	-	ASTM D6866

MAIN APPLICATIONS:

- Fluid transportation
- Air brake line
- Fuel line
- Tubing for use in motor vehicle

PACKAGING:


This grade is delivered dried in sealed packaging (25 kg bags, 44 lb bags, 550 kg rigid containers, 1000 lb rigid containers) ready to be processed.

SHELF LIFE:


Two years from the delivery. For any use above this limit, please refer to our technical services.

DIAGRAMS

VISCOSITY-SHEAR RATE



SHEARSTRESS-SHEAR RATE




Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>


RILSAN®
BY ARKEMA

RILSAN® BESNO P40 TL


DYNAMIC SHEAR MODULUS-TEMPERATURE




STRESS-STRAIN



SECANT MODULUS-STRAIN



STRESS-STRAIN (ISOCHRONOUS) 23°C




Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SDC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>


RILSAN®
BY ARKEMA

RILSAN® BESNO P40 TL


CREEP MODULUS-TIME 23°C




STRESS-STRAIN (ISOCRONOUS) 100°C



CREEP MODULUS-TIME 100°C



SPECIFIC VOLUME-TEMPERATURE (PVT)



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 280°C.
- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-8 hours at 80-90°C.

PROCESSING

Profile Extrusion, Other Extrusion

DELIVERY FORM

Pellets

SPECIAL CHARACTERISTICS

Bio-Based, Heat Stabilized, Light Stabilized

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

RILSAN®
BY **ARKEMA**

RILSAN® BESNO P40 TL

ADDITIVES

Lubricants, Plasticizer

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

[rilsan.com](https://www.rilsan.com)

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
[arkema-america.com](https://www.arkema-america.com)

RILSAN®
BY ARKEMA

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
[arkema.com](https://www.arkema.com)