

# RILSAN® FINE POWDERS 5913 BLUE RDP 15-10 FB

## Rilsan® 5913 Blue Fluid Bed Powder

Rilsan® fluid bed powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

## MAIN CHARACTERISTICS

| PROPERTIES                                               | VALUE       | UNIT              | TEST STANDARD |
|----------------------------------------------------------|-------------|-------------------|---------------|
| <b>POWDER PROPERTIES</b>                                 |             |                   |               |
| Color                                                    | Blue        | -                 | -             |
| Melting Temperature                                      | 183 - 193   | °C                | ISO 1218      |
| <b>POWDER COATING PROPERTIES</b>                         |             |                   |               |
| Covering Efficiency , 300µm                              | 0.35        | kg/m <sup>2</sup> | -             |
| Specific Gravity of Coating, 20°C                        | 1.12 - 1.18 | -                 | ISO 1183      |
| Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles | ≤20         | mg                | ASTM D1044    |
| Impact Resistance                                        | 160         | J                 | ASTM D2794    |

## MAIN APPLICATIONS:

- coating of wire goods and piping components exposed to high weathering or corrosive environments
- Rilsan® fluid bed powders are designed to coat metal substrates via fluidized powder bed dipping
- Good adhesion after over 2000 hours of salt spray testing (ISO 9227)
- Only 0.1% coarse particles > 254 µm (ASTM D3451)
- For more information visit: [www.rilsanfinepowders.com](http://www.rilsanfinepowders.com)
- coating of machinery exposed to high abrasion such as spline shafts
- Additional info
- Only 20% fine particles < 75 µm (ASTM D3451)
- 5 year shelf life from date of manufacture
- coating of springs for sound reduction
- Smooth texture with a glossy appearance
- Only 1% coarse particles > 212 µm (ASTM D3451)
- Available in 100 lb drums

## PROCESSING

Coating, Fluidized Bed Dipping

## DELIVERY FORM

Powder

## REGIONAL AVAILABILITY

North America

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® FINE POWDER is a registered trademark of Arkema  
© 2022 Arkema Inc. All rights reserved.

[rilsanfinepowders.com](http://rilsanfinepowders.com)

**Arkema Inc. – Technical Polymers**  
900 First Avenue  
King of Prussia, PA 19406  
Tel.: +1 610 205 7000  
Fax: +1 610 205 7497  
[arkema-america.com](http://arkema-america.com)

**RILSAN®**  
FINE POWDERS  
BY **ARKEMA**

**Headquarters: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
Tel.: +33 1 49 00 80 80  
Fax: +33 1 49 00 83 96  
[arkema.com](http://arkema.com)

Arkema France – A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018