

RILSAN® FINE POWDERS MINICOAT WHITE 1452 MAC

Rilsan® MINICOAT WHITE 1452 MAC resin - Rilsan® POLYAMIDE 11 (PA11) powder

Melt mix white powder for coating of small metallic parts using Arkema's Minicoat process. The range includes several colors. The properties listed in the data base have been measured on a corresponding Rilsan® PA11 granule.

For more information visit: www.rilsanfinepowders.com

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	185	°C	ISO 11357-1/-3
Vicat Softening Temperature, 50°C/h 50N	160	°C	ISO 306
Burning Behav. at 1.5 mm Nominal Thickness	V-2	class	IEC 60695-11-10
Thickness Tested	1.6	mm	-
Burning Behav. at Thickness h	V-2	class	IEC 60695-11-10
Thickness Tested	3.2	mm	-
ELECTRICAL PROPERTIES			
Volume Resistivity	1E12	Ohm*m	IEC 60093
Surface Resistivity	1E14	Ohm	IEC 60093
Dielectric (Electric) Strength	30	kV/mm	IEC 60243-1
OTHER PROPERTIES			
Water Absorption	1.9	%	Sim. to ISO 62
Density	1100	kg/m³	ISO 1183
POWDER PROPERTIES			
Color	White	-	-

PROCESSING

Coating, Minicoat/Maxicoat

DELIVERY FORM

Powder

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® FINE POWDER is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsanfinepowders.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

RILSAN®
FINE POWDERS
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018