

# RILSAN® FINE POWDERS T WHITE 7279S

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

## MAIN CHARACTERISTICS

| PROPERTIES                                                             | VALUE                          | UNIT              | TEST STANDARD |
|------------------------------------------------------------------------|--------------------------------|-------------------|---------------|
| <b>THERMAL PROPERTIES</b>                                              |                                |                   |               |
| Vicat Softening Temperature, 50°C/h 50N                                | 181                            | °C                | ISO 306       |
| <b>POWDER PROPERTIES</b>                                               |                                |                   |               |
| Color                                                                  | White                          | -                 | -             |
| Particle Size Distribution, ≤ 40µm                                     | 2                              | %                 | ISO 13320     |
| Particle Size Distribution, ≥ 254µm                                    | 3                              | %                 | ISO 13320     |
| Particle Size Distribution, Median Size                                | 100 - 130                      | µm                | ISO 13320     |
| Melting Temperature                                                    | 183 - 188                      | °C                | ISO 1218      |
| Vicat Point                                                            | 181                            | °C                | ISO 306       |
| Non Tapped Density                                                     | 0.54                           | -                 | ISO 1068      |
| Tapped Density                                                         | 0.66                           | -                 | ISO 1068      |
| Fluidized Density                                                      | 0.5                            | -                 | -             |
| <b>POWDER COATING PROPERTIES</b>                                       |                                |                   |               |
| Recommended Coating Thickness                                          | ≥250                           | µm                | -             |
| Covering Efficiency, 300µm                                             | 0.36                           | kg/m <sup>2</sup> | -             |
| Specific Gravity of Coating, 20°C                                      | 1.1                            | -                 | ISO 1183      |
| Persoz Hardness                                                        | 225                            | -                 | ISO 1522      |
| Shore D Hardness                                                       | 74                             | -                 | ISO 868       |
| Water Absorption, 24h                                                  | ≤1                             | %                 | ISO 62-1      |
| Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles               | 30                             | mg                | ISO 9352      |
| Impact Resistance                                                      | ≥2                             | J                 | ASTM G14      |
| Salt spray test according to surface preparation recommended by ARKEMA | Good adhesion after 2000 hours | -                 | ISO 9227      |

## MAIN APPLICATIONS

- Metal Coating
- General Purpose

## PACKAGING

This grade is delivered in 25 kg bags.

## SHELF LIFE

Five years from the date of delivery. For any use after this limit, please refer to our technical services.

## PROCESSING

Coating, Fluidized Bed Dipping

## DELIVERY FORM

Powder

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

**RILSAN®**  
FINE POWDERS  
BY ARKEMA

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SBC/11-2018

# RILSAN® FINE POWDERS T WHITE 7279S

Arkema France - A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790  
SIC/11-2018

Please consult Arkema's disclaimer regarding the use of Arkema's products on  
<https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® FINE POWDER is a registered trademark of Arkema  
© 2022 Arkema Inc. All rights reserved.

[rilsanfinepowders.com](https://rilsanfinepowders.com)

#### Arkema Inc. – Technical Polymers

900 First Avenue  
King of Prussia, PA 19406  
Tel.: +1 610 205 7000  
Fax: +1 610 205 7497  
[arkema-america.com](https://arkema-america.com)

**RILSAN®**  
FINE POWDERS  
BY ARKEMA

#### Headquarters: Arkema France

420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
Tel.: +33 1 49 00 80 80  
Fax: +33 1 49 00 83 96  
[arkema.com](https://arkema.com)