

RILSAN® FINE POWDERS TECHLINE WHITE 7601

Rilsan® 7601 Techline White Minicoat/ Maxicoat Powder

Rilsan® minicoat/ maxicoat powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
POWDER PROPERTIES			
Color	White	-	-
Particle Size Distribution, Median Size	30 - 60	μm	ISO 13320
Melting Temperature	183 - 188	°C	ISO 1218
Non Tapped Density	0.44	-	ISO 1068
Tapped Density	0.57	-	ISO 1068
POWDER COATING PROPERTIES			
Covering Efficiency , 200μm	0.22	kg/m ²	-
Specific Gravity of Coating, 20°C	1.11	-	ISO 1183
Persoz Hardness	270	-	ISO 1522
Water Absorption, 24h	≤1	%	ISO 62-1
Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles	8	mg	ISO 9352

MAIN APPLICATIONS:

- coating of small items such as undergarment clips
- stamped metal
- fasteners
- and boot eyelets
- small automotive parts
- Rilsan® minicoat/ maxicoat powders are designed to coat small parts with metal substrates via the minicoat or maxicoat process. The Techline White grade is designed for further pigmentation to create a wide spectrum of colors
- Good adhesion after over 2000 hours of salt spray testing (ISO 9227)
- 5 year shelf life from date of manufacture
- Additional info
- Only 10% fine particles < 20 μm (ISO 13320)
- Available in 20 kg bags- For more information visit: www.rilsanfinepowders.com
- Smooth texture with a glossy appearance
- Only 6% coarse particles > 80 μm (ISO 13320)

PROCESSING

Coating, Fluidized Bed Dipping

DELIVERY FORM

Powder

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® FINE POWDER is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsanfinepowders.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-americas.com

RILSAN®
FINE POWDERS
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme" registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018