

RILSAN® FINE POWDERS WHITE RDP 21 FB

Rilsan® White Fluid Bed Powder

Rilsan® fluid bed powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

MAIN CHARACTERISTICS

PROPERTIES	VALUE	UNIT	TEST STANDARD
POWDER PROPERTIES			
Color	White	-	-
Melting Temperature	183 - 193	°C	ISO 1218
POWDER COATING PROPERTIES			
Covering Efficiency , 300µm	0.36	kg/m ²	-
Specific Gravity of Coating, 20°C	1.18	-	ISO 1183
Abrasion Resistance, Wheel CS 17, load 1 kg, 1000 cycles	20	mg	ASTM D1044
Impact Resistance	160	J	ASTM D2794

MAIN APPLICATIONS:

- coating of wire goods and piping components exposed to high weathering or corrosive environments
- Rilsan® fluid bed powders are designed to coat metal substrates via fluidized powder bed dipping
- Good adhesion after over 2000 hours of salt spray testing (ISO 9227)
- Only 0.1% coarse particles > 250 µm (ASTM D3451)
- For more information visit: www.rilsanfinepowders.com
- coating of machinery exposed to high abrasion such as spline shafts
- Additional info
- Only 15% fine particles < 75 µm (ASTM D3451)
- 5 year shelf life from date of manufacture
- coating of springs for sound reduction
- Smooth texture with a glossy appearance
- Only 1% coarse particles > 212 µm (ASTM D3451)
- Available in 100 lb drums

PROCESSING

Coating, Fluidized Bed Dipping

DELIVERY FORM

Powder

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® FINE POWDER is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsanfinepowders.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

RILSAN®
FINE POWDERS
BY **ARKEMA**

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France – A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S00711-2018