

RILSAN® SMNO F

Rilsan® SMNO F resin - Rilsan® POLYAMIDE 610 (PA610)

Rilsan® SMNO F is an undried polyamide 610 resin produced partially from a renewable source. This natural grade is designed for compounding applications.

Percentage of renewable carbon according to ASTM D 6866: **>60%**.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	1700 / -	MPa	ISO 527-1/-2
Charpy Impact Strength, +23°C	No Break / -	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	No Break / -	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	7 / -	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	5 / -	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Temp. of Deflection Under Load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
OTHER PROPERTIES			
Density	1080 / -	kg/m ³	ISO 1183
%Bio-Based	60	-	ASTM D6866

SPECIAL CHARACTERISTICS

Bio-Based

REGIONAL AVAILABILITY

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Rilsan® is a registered trademark of Arkema
© 2022 Arkema Inc. All rights reserved.

rilsan.com

Arkema Inc. – Technical Polymers
900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

RILSAN®
BY ARKEMA

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 S0C/11-2018