

【Inquiries】

AsahiKASEI Engineering Plastics Information Comprehensive Site
URL : <https://www.asahi-kasei-plastics.com/en/contact/>

AsahiKASEI



LEONA™ 14G30 *33D4

Asahi Kasei Corporation - Polyamide 66

Tuesday, March 19, 2024

General Information

General

Material Status	• Commercial: Active ¹
Availability	• Africa & Middle East • Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer
Features AKEP website	• Heat Stabilized
Uses	• Automotive Applications • Automotive Under the Hood • Electrical/Electronic Applications • Structural Parts
Automotive Specifications	• FORD WSK-M4D752-A Color: BK • GM GMP.PA66.040 Color: BK • GM GMW3038P-PA66-GF30H Color: BK • GM GMW3038P-PA66-GF30J Color: BK
Part Marking Code (ISO11469) (ISO 11469)	• >PA66-GF30<

Other Documentation

Literature	• Moldflow Data • Molding Conditions • SDS • Technical Handbook
------------	--

ASTM & ISO Properties ²

Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.0	--	%	
Flow	0.40	--	%	
Water Absorption				ISO 62
Equilibrium, 23°C, 50% RH	--	1.8	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	10500	7400	MPa	ISO 527-1
Tensile Stress (Break, 23°C)	202	135	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.0	6.0	%	ISO 527-2
Flexural Modulus (23°C)	9400	7100	MPa	ISO 178
Flexural Stress (23°C)	300	218	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	13	16	kJ/m ²	ISO 179

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

LEONA™ 14G30 *33D4

Asahi Kasei Corporation - Polyamide 66

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	260	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	251	--	°C	ISO 75-2/A
CLTE				ASTM D696
Flow : 23 to 55°C	3.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	9.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength	43	--	kV/mm	IEC 60243-1
Comparative Tracking Index	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.75 mm)	HB	--		UL 94

Processing Information

Injection	Dry	Unit
Drying Temperature - Vacuum Dryer	80 to 90	°C
Drying Time - Vacuum Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	275 to 295	°C
Mold Temperature	75 to 85	°C

Notes

¹ * is an optional alphabet which differs depending on production location.

² Typical properties: these are not to be construed as specifications.

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.