

【Inquiries】

AsahiKASEI Engineering Plastics Information Comprehensive Site
URL : <https://www.asahi-kasei-plastics.com/en/contact/>

AsahiKASEI



Stylac™ IC10N

Asahi Kasei Corporation - Acrylonitrile Butadiene Styrene

Tuesday, March 19, 2024

General Information

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe
Additive	• Antistatic
Uses	• Industrial Applications

Other Documentation

Literature	• SDS
------------	-----------------------

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	1.6	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	1.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow	0.10 to 0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	133	MPa	ISO 527-2/5
Flexural Modulus ²	10000	MPa	ISO 178
Flexural Stress ²	186	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	100	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306/B
Thermal Conductivity	0.26	W/m/K	ASTM C177
RTI Elec	60.0	°C	UL 746B
RTI Imp	60.0	°C	UL 746B
RTI Str	60.0	°C	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	4.0	ohms	ASTM D257
Volume Resistivity	0.50	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	HB		UL 94

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

Stylac™ IC10N

Asahi Kasei Corporation - Acrylonitrile Butadiene Styrene

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min



Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.