

【Inquiries】

AsahiKASEI Engineering Plastics Information Comprehensive Site
URL : <https://www.asahi-kasei-plastics.com/en/contact/>

AsahiKASEI



TENAC™-C MT754

Asahi Kasei Corporation - Acetal (POM) Copolymer

Tuesday, March 19, 2024

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Mineral, 20% Filler by Weight		
Features AKEP website	• Flow, High	• Warpage, Low	
Uses	• Engineering Parts	• Gears	• Housings
Part Marking Code (ISO11469) (ISO 11469)	• >POM-MD20<		

Other Documentation

Literature	• Molding Conditions • SDS • Technical Handbook
------------	---

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.58	g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.0 to 1.2	%	Internal Method
Water Absorption (24 hr, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4800	MPa	ISO 527-1
Tensile Stress			
Break	61.0	MPa	ISO 527-2
--	60.0	MPa	ASTM D638
Tensile Elongation			
Break	7.0	%	ASTM D638
Break	5.0	%	ISO 527-2
Flexural Modulus			
--	5000	MPa	ASTM D790
--	4800	MPa	ISO 178
Flexural Strength	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.0	kJ/m ²	ISO 179
Notched Izod Impact	39	J/m	ASTM D256

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.

TENAC™-C MT754**Asahi Kasei Corporation - Acetal (POM) Copolymer**

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	98		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	163	°C	ASTM D648
0.45 MPa, Unannealed	161	°C	ISO 75-2/B
1.8 MPa, Unannealed	150	°C	ASTM D648
1.8 MPa, Unannealed	131	°C	ISO 75-2/A
CLTE - Flow	6.0E-5	cm/cm/°C	ASTM D696 ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.75 mm	HB		
1.5 mm	HB		

Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature - Hot Air Dryer	80 to 90	°C	
Drying Time - Hot Air Dryer	3.0 to 4.0	hr	
Processing (Melt) Temp	180 to 210	°C	
Mold Temperature	> 60	°C	

Notes

¹ Typical properties: these are not to be construed as specifications.

Disclaimer:

- Data shown are typical values obtained by proper testing methods and should not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.

These data may be changed because of improvement in properties.

- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

- Do not use plastics in any of the following orally- or medically-related applications.

- Orally-related applications: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.

For drinking water application, please consult Asahi Kasei Corporation.

- Medically-related applications: any part, device or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids or transfusion fluids.